LANE MOUNTAIN COMPANY LM FOOTING SAND



DATA SHEET

Product Description

Finely blended silica sand with ideal sizing and compaction for new or existing horse arenas

Screen Analysis (Typical) – individual results will vary

% Retained 30 mesh:	0.2%
% Retained 40 mesh:	3.3%
% Retained 50 mesh:	9%
% Retained 70 mesh:	11%
% Retained 100 mesh:	17.5%
% Retained 140 mesh:	35%
% Retained 200 mesh:	14%
% Retained PAN:	10%

Physical Properties (Typical)

Color:	White/Off White
Specific gravity:	2.65
Moisture:	8-12%

For more information on our products, please contact:

Lane Mountain CompanyProduction Facility:Tim Hemphill, VPLane Mountain Company206-941-4996 (cell)3119 Highway 231tim @lanemt.comValley, WA 99181509-937-2221

The data above is based on average results on production samples. Product shipments are subject to normal variation. Test data does not guarantee minimum or maximum specifications.